

DATASHEET

Trade Code: C11MA

Material: PA/PE

Product Name: Coextruded Film for Vacuum Application

Typical Value

Gauge μm	Yield m ² /g	Tensile Strength MPa		Elongation %		Haze %	Seal Strength N/15mm	Cof	OTR cc/m ² .d.bar (23°C,dry)	WVTR g/m ² .d (38°C, 90%RH)
		MD	TD	MD	TD					
ASTM F2251	/	ASTM D882		ASTM D882		ASTM D1003	ASTM F88	ASTM D1894	ASTM D3985	ASTM F1249
65	0.0161	28	26	400	400	15.0	20	0.25	75	6.5
70	0.0149	28	26	400	400	16.0	21	0.25	70	6.0
75	0.0139	28	26	400	400	17.0	22	0.25	65	5.5
80	0.0131	27	25	400	400	18.0	23	0.25	60	5.0
90	0.0116	27	25	400	400	20.0	25	0.25	55	4.5
95	0.0110	27	25	400	400	21.0	26	0.25	50	4.0
100	0.0105	26	24	400	400	22.0	27	0.25	50	4.0
120	0.0087	26	24	400	400	26.0	30	0.25	40	3.0
125	0.0084	26	24	400	400	28.0	32	0.25	40	3.0

Application: This product can be frozen or boiled in water and the recommended application temperature is from -18 °C to 105 °C.

If you have any further questions or need to know about this product, please contact with our salesperson.

Compliance: This product complies with FDA, EU and Chinese regulations on food materials for direct food contact applications. Contact with us for more information about food contact safety.

Storage: This product should be stored in clean, cool, dry and dark conditions. Sunrise recommends our customers using these products within two years.

Declaration: The technical data contained herein is based on Sunrise internal testing results and believed to be reliable. Users should make their own judgment and determination of the suitability for their intended applications. Sunrise assumes no liability whatsoever in connection with the use of information.